



## CONSERVATION BY DESIGN LIMITED

Timecare Works  
5 Singer Way  
Woburn Rd Ind. Estate  
Kempston  
Bedford  
MK42 7AW  
Great Britain

Tel: (01234) 853555  
Fax: (01234) 852334  
Email [info@conservation-by-design.co.uk](mailto:info@conservation-by-design.co.uk)  
Web: <http://www.conservation-by-design.co.uk>

## TECHNICAL DATA

### Beva 37I Film ( AD8F / AD9F )

#### Composition:

Pure Beva 37I solution in a film form

#### Description:

Beva 37I comes sandwiched between a white silicone - coated paper and a mylar ( polyester ) release sheet. The transparent support allow:

- the film to be cut precisely to any shape
- the film to be inserted into loose areas
- delaminating paint to be properly aligned

all before the film is heat activated.

#### Application & users tips ( also see instructions for Beva Gel )

Beva 37I Film should be applied at 65° C using either a heated spatula, a laminating / vacuum press or hot air jet. Some conservators have experimented with temperatures as low as 40° C, finding that the film will adhere after being mist sprayed with white spirit. However please note that extreme caution needs to be taken with this technique to avoid excess fumes from the white spirit and / or the possibility of ignition.

#### Reversibility:

Beva 37I Film can be removed from absorbent surfaces using hexane, toluene or acetone provided that:

- these solvents do not damage the art work involved
- appropriate health and safety restrictions are applied.

Beva 37I Film can also be reversed by heat and low aromatic petroleum solvents.

**Order Details:**

Beva 371 Film is available as either

- **AD8F** • 27" ( 690 mm ) x 349.9" ( 1 metre )
- **AD9F** • 27" ( 690 mm ) x 32.8 ft. ( 10 metre ) rolls.

For further information call + 44 ( 0 ) 1234 853 555 or fax + 44 ( 0 ) 1234 852 334